



ZELL-METALL Ges.m.b.H.  
 Schulstraße 511  
 A-5710 KAPRUN AUSTRIA/EUROPE  
 Tel: +43 6547 8417 / Fax: +43 6547 8890  
 E-mail: zell-metall@zmk.at  
 Internet: www.zell-metall.com



09/2006

## TECHNICAL PROPERTIES OF ZELLAMID<sup>®</sup>

Property	Unit	Test method	Condition of specimen	ZELLAMID <sup>®</sup> 202 (PA6)	ZELLAMID <sup>®</sup> 250 (PA6.6)	ZELLAMID <sup>®</sup> 250 GF 30 (PA6.6+30% Glassfibre)	ZELLAMID <sup>®</sup> 900 900SW (POM-C)	
<b>MECHANICAL PROPERTIES</b>								
Tensile strength at break	MPa	ISO 527	dry	80	80	100	70	
	MPa	ISO 527	moist	50	60	-	-	
Elongation at break	%	ISO 527	dry	50- 100	50	8	40	
	%	ISO 527	moist	200	150	-	-	
Modulus of elasticity in tension	MPa	ISO 527	dry	3000	3200	4800	3000	
	MPa	ISO 527	moist	1500	1600	-	-	
Charpy Impact strength	+ 23°C	ISO 179/1eU	dry	no break	no break	20	no break	
	- 40°C	ISO 179/1eU	dry	no break	no break	-	80	
Charpy Impact strength (notched)	kJ/m <sup>2</sup>	ISO 179/1eA	dry	70	80	-	-	
	kJ/m <sup>2</sup>		moist	-	-	-	-	
Hardness Shore, scale D		ISO 868	dry	75	80	85	81	
Time yield limit $\sigma_{1/1000}$	23°C/50% RH	ISO 899	moist	5.5	6.0	-	14	
	100°C	ISO 899	dry	2.5	3.5	-	-	
Apparent modulus $E_{C/1000 20}$	23°C/50% RH	ISO 899	moist	230	400	-	-	
<b>THERMAL PROPERTIES</b>								
Heat distortion temperature, ISO 75	Method A	ISO 75	dry	55 – 75	100	250	110	
	Method B	ISO 75	dry	> 160	> 200	250	160	
Melting point	Method A	ISO 3146	-	220	255	255	164-168	
Maximum service temperature for few hours operation		-	-	≤ 180	≤ 200	200	-	
TEP 5 000 hours (50% of tensile strength) 4)		IEC 216	-	90	95	-	-	
TEP 20 000 hours (50% of tensile strength) 4)		IEC 216	-	75	80	-	100	
Thermal coefficient of linear expansion		DIN 53452	dry	7– 10	7– 10	2 - 3	11	
Thermal conductivity	Method A		dry	0.23	0.23	0.27	-	
Specific heat		IEC 1006	dry	1.7	1.7	1.5	1.5	
<b>DIELECTRIC PROPERTIES</b>								
Dielectric constant	1 MHz		dry	3.5	3.2	-	3.8	
			moist	7.0	5.0	-	-	
Dissipation factor tan $\delta$	1 MHz		dry	0.023	0.026	-	0.024	
			moist	0.3	0.2	-	-	
Dielectric strength	KV/mm	IEC 243	dry	100	120	30	> 20	
	KV/mm	IEC 243	moist	60	80	-	-	
Volume resistivity	$\Omega \cdot \text{cm}$	IEC 93	dry	10 <sup>15</sup>	10 <sup>15</sup>	> 10 <sup>12</sup>	10 <sup>15</sup>	
	$\Omega \cdot \text{cm}$	IEC 93	moist	10 <sup>12</sup>	10 <sup>12</sup>	-	-	
Surface resistivity	$\Omega$	IEC 93	dry	10 <sup>13</sup>	10 <sup>13</sup>	10 <sup>11</sup>	-	
	$\Omega$	IEC 93	moist	10 <sup>10</sup>	10 <sup>10</sup>	-	-	
Resistance to tracking	KA/ KB method	IEC 112	dry/moist	KB > 600	KB >600	-	KB >600	
	KC method	IEC 112	dry/moist	KC > 600	KC > 600	-	-	
<b>MISCELLANEOUS PROPERTIES</b>								
Mass density	Method D, E	g/cm <sup>3</sup>	ISO 1183	dry	1.13– 1.15	1.13– 1.15	1.35	1.41-1.43
Moisture absorption at 23°C, 50% RH	Saturation	%	ISO 1110	-	3.0±0.4	2.8±0.3	1.5	0.20
Water absorption at 23 °C	Saturation	%	ISO 62	-	9.5±0.5	8.5±0.5	5.5	0.25
Fire performance	Flameability Acc. VDE		VDE 0304	dry	II b	II b	-	BH3-25mm/min
	Flameability of interior materials in passenger cars h>1mm	mm/min	FMVSS 302	moist	< 100	< 100	-	-
	Flameability according UL (thickness of specimen 1,6 mm)	-	UL 94	-	HB	HB	HB	HB
Resistance to wear <sup>5)</sup>		$\mu\text{m}/\text{km}$	ISO 7148-2	dry	-	-	-	-

1. Dry= dried at 80°C and 1 mbar until weight is constant (moisture content less than 0.2%)
2. Moist=after storage in a standard atmosphere of 23° C and 50% relative humidity (DIN 50014) until saturation.
3. pecimen boxes, thickness t=1.5 mm
4. Data of the resin only
5. Made by a pin / rotating disc test according DIN-ISO 7148-2 under following conditions:  $R_s = 0,35 - 0,45 \mu\text{m}$  (steel disc),  $v = 0,3 \text{ m/s}$ ,  $p = 3 \text{ N/mm}^2$ , time  $T > 16\text{h}$

All information are without warranty and liability.